

Liquid

Fun and fresh and dripping with seductive style, Liquid leather look as if it just stepped out of the shower. Aniline dyed, pearlized and patterned like fingerprints or windswept sand, the patent solution is baked on for 48 hours. The resulting glossy surface appears wet and is lightly milled for an airy finish. Available in several neutral colors or daring shades of red and purple.

Hide Origin	Europe
Country Finished	Italy
Average Hide Size	20 SF
Thickness	1.0-1.2 mm
Dye Method	Aniline
Finish	Spilltop® Water Resistance
Light Fastness (EN ISO 105-B02)	4
Cigarette Ignition Resistance (NFPA 260)	Class 1
IMO 2010 Part 8 [IMO RES. A652 (16)]	
Smoldering Cigarette (3.1)	Passes
Propane Flame (3.2)	Passes
Spilltop Water Resistance	
AATCC Test Method 22-2010	100 (ISO 5)



SPILLTOP leather is rated 90-100 with minimal-to-no sticking or wetting of the article's surface.

- 100 – No sticking or wetting of specimen face
- 90 – Slight random sticking or wetting of specimen face
- 80 – Wetting of specimen face at spray points
- 70 – Partial wetting of specimen face beyond spray points
- 50 – Complete wetting of the entire specimen face beyond spray points
- 0 – Complete wetting of the entire face of the specimen

CARE & CLEANING

Routine dusting or vacuuming is encouraged. To add luster and longevity, rotate article periodically and avoid direct sunlight. For spills, gently blot area with cloth or sponge without applying force. If needed, dampen cloth or sponge with warm water. Do not use a hair dryer. Do not use saddle soap, solvents, oils, polishes, varnishes, detergents, bleach or ammonia.